

OTHER ALLOYS

Advamet® Copper Datasheet

Advamet® is a wax/polymer binder system;
Compliant to MPIF Standard 35: MIM-Copper

Typical Chemical Composition (post Sinter)

Cu (%)
99.8 -100

Typical Particle Size Distribution

d_{90}
-22micron

Typical Physical Properties

Mechanical	Density	Thermal Conductivity (@ 77°F)	UTS	YS	Elongation
Units	(g/cm ³)	Btu *ft/(h*ft ² * °F)	(ksi)	(ksi)	(in./in.)
As-sintered	8.75	208	30	10	30

Coefficient of Thermal Expansion	Average CTE {x10 ⁶ /°F}
From Room Temp. to 100° F	8.7
From 101 ° F to 150° F	8.9
From 151 ° F to 200° F	9.1
From 201 ° F to 250° F	9.3
From 251 ° F to 300° F	9.4

Actual results depend on processing, including sintering cycle - performed.



4511 W. 99th St., Carmel, IN 46032 USA
Phone: 317-337-0441