

SOFT-MAGNETIC ALLOYS

Advamet® or Advacat® 2200 Datasheet

Advamet® is a wax/polymer binder system;

Advacat® is a POM based (catalytic) binder system.

Both systems are compliant to MPlF Standard 35: MIM-2200

Typical Chemical Composition (post Sinter)

C (%)	Ni (%)	Si (%)	Fe (%)
0.1 max	1.5-2.5	1.0 max	balance

Other elements not to exceed 1.0% combined.

All percentages are in weight percent.

Typical Mechanical Properties

Nominal Typical Values	Density	UTS	YS	Elongation	Mag. Perm	H _c	B _r	B ₂₅	B ₅₀₀
	(g/cm ³)	(ksi)	(ksi)	(in./in.)	μ max	Oe	kG	kG	kG
As-sintered	7.65	42	18	40	2,300	1.5	8.0	14.5	20.0

Actual results depend on processing – sintering and heat treatment cycles – used.



4511 W. 99th St.,
Carmel, IN 46032 USA
317-337-0441
info@ampmim.com

